

Variation of the glass transition temperature with rigidity and chemical composition

Gerardo G. Naumis

*Instituto de Física, Universidad Nacional Autónoma de México (UNAM),
Apartado Postal 20-364, 01000, México, Distrito Federal, Mexico.*

(Dated: February 2, 2008)

The effects of rigidity and chemical composition in the variation of the glass transition temperature are obtained by using the Lindemann criteria, that relates melting temperature with atomic vibrations. Using this criteria and that floppy modes at low frequencies enhance in a considerable way the average quadratic displacement, we show that the consequence is a modified glass transition temperature. This approach allows to obtain in a simple way the empirically modified Gibbs-DiMarzio law, which has been widely used in chalcogenide glasses to fit the changes in the glass transition temperature with the chemical composition. The method predicts that the constant that appears in the law depends upon the ratio of two characteristic frequencies (or temperatures). Then, the constant for the $Se_{1-x-y}Ge_xAs_y$ glass is estimated by using the experimental density of vibrational states, and the result shows a very good agreement with the experimental fit from glass transition temperature variation.

PACS numbers: 64.70.Pf, 64.60.-i, 05.70.-a, 05.65.+b

Glasses are solids that do not have long range order, and which are usually produced by fast cooling of a liquid melt. In spite of the well known importance of these materials in human history, the physics of glass formation is still an open and puzzling problem [1]. The reason behind this situation is that glass formation is mainly a non-equilibrium process, and thus even some important questions for glass technology are not well understood, as the origin of the non-exponential relaxation laws [2] or the ability of certain materials to reach the glassy state [3]. The first approach to the problem was made by Kauzmann [4], who pointed out that there is an underlying thermodynamical phase transition behind glass formation due to an entropy crisis. Although the Kauzmann approach was very successful, it was unable to answer many questions, specially in a quantitative way. Later on, other approaches were proposed [5]: phenomenological models like the Gibbs-DiMarzio, theories based in supercooled liquids as for example mode coupling and energy landscape formalism, or the use of extensive computer simulations [4]. However, most of these theories have difficulties to explain one of the most simple and interesting questions: how the glass transition temperature (T_g) depends on chemical composition. As discovered by the Phoenicians more than 2,000 years ago, T_g can be dramatically lowered or raised by adding few impurities. Another interesting property of glasses is the behavior of viscosity, which is usually referred as fragility [6]. Fragility is related to the glass forming tendency, since a non-fragile glass former do not require a high speed of cooling to be produced. The fragility of the glass can be changed from strong to fragile [6]. Chalcogenide glasses (formed with elements from the VI column doped with impurities) are very important to understand these effects. In general, the change of T_g with the chemical composition has been observed to follow an empirically modified Gibbs-DiMarzio law [6][7][8][9]. It is worthwhile mentioning that the original Gibbs-DiMarzio

law was developed for polymers [4], and contains some special assumptions that have been very elusive to measure, like the size of cooperative rearranging regions [4]. Furthermore, the use of this law for chalcogenide glasses is based in the hypothesis that these glasses nearly behave as polymers. A completely different approach is to use stochastic matrices [10, 11][12]. The problem with this theory is that one needs to assume certain conditions to define the glass transition which are not in the form of usual definitions [10].

The rigidity theory (RT), introduced by Phillips [13] and refined by Thorpe [14], was another important step to understand glass formation. By considering the covalent bonding as a mechanical constraint, the ease of glass formation is related with the ratio between available degrees of freedom and the number of constraints. If the number of constraints is lower than the degrees of freedom, there are zero frequency vibrational modes called floppy [15]. The resulting network is under-constrained. A transition occurs when a disordered lattice becomes rigid. Glasses that are rigid at a certain chemical composition are easier to form, and many features of this transition have been experimentally observed [8][16]. Even for simple systems like hard-disks [17], polymer melts [18], and colloids [19], rigidity plays an important role. For more complex systems like proteins, RT is a very powerful tool to understand folding and long-time scale motions [20]. Recently, it has been discovered that at the rigidity transition, there is a window of thermodynamical reversibility [8][21][22][23], explained as a self-organization of the stress in the network [24][25]. Although RT explains a lot of the phenomenology of chalcogenide glasses, the introduction of thermodynamics into RT has been elusive [18]. In previous papers, we approached some of these problems by using a phenomenological free energy [26], and then we made computer simulations [27][28]. Yet, many questions remain open, as for example the variation of T_g with the chemical composition of the glass.

In this letter, we will show that by using the RT and the old Lindemann criteria that relates melting with the size of atomic vibrations (which has been proved to be valid for glasses [29][30]), one can explain the variation of T_g with chemical composition, and obtain in a simple and elegant way the modified empirical Gibbs-DiMarzio law. Furthermore, it provides a clear path to understand glass transition trends with the connectivity of the network.

In RT, the ability for making a glass is optimized when the number of freedom degrees, $3N$, where N is the number of particles, is equal to the number of mechanical constraints (N_c) that are given by bond bending and stretching forces. The parameter $f = (3N - N_c)/3N$ gives the fraction of cyclic variables of the Hamiltonian. A variation of these coordinates do not change the energy and thus f also corresponds to the fraction of vibrational modes with zero frequency, called floppy modes [14], with respect to the total number of vibrational modes. The parameter f is in fact a function of the average chemical coordination of the glass, and can be calculated using the pebble game algorithm [15], but usually it can be estimated with a mean-field procedure, known as Maxwell counting [31],

$$f = \frac{3N - N_c}{3N} = 2 - \frac{5}{6} \langle r \rangle$$

where $\langle r \rangle$ is the average coordination number, defined as,

$$\langle r \rangle = \sum_{r=0}^{Z_{\max}} r x_r$$

and r is the coordination number of each atomic specie. x_r is the occurrence of each type of atom [31]. A rigidity transition occurs when $f = 0$, and the system passes from a floppy network to a rigid one. Glasses are rigid if there are more constraints than degrees of freedom, and then the lattice is overconstrained. In 3D, the rigidity transition leads to the critical value $\langle r_c \rangle = 2.4$ if all angular constraints are considered [31]. In principle, since floppy modes have zero frequency; they do not contribute to the elastic energy, and the specific heat of the glass depends on f , a result that violates the Dulong-Petit law [26], and which is not observed in the experimental data [8]. In fact, floppy modes do not have a perfect zero frequency, *i.e.*, in real glasses they are shifted by residual forces, like the Van der Waals interaction [14]. This is confirmed by neutron scattering experiments, where it has been shown that floppy modes in the prototypical compound $Se_{1-x-y}Ge_xAs_y$ are blue-shifted [16][32][33], forming a peak around $5meV$. The corresponding temperature (Θ_f) where these modes are frozen, can be estimated from the energy required to excite modes of $5meV$, that gives $\Theta_f \approx 54^\circ K$. For low temperatures, is clear that floppy modes are important, as confirmed by the giant-softening of the $119Sn$ Lamb-Mossbauer factor in $(Ge_{0.99}Sn_{0.01})_x Se_{1-x}$ glasses [16]. But in principle, one can argue that floppy modes are not so important for the physics of the glass at high temperatures, since

all $3Nf$ floppy oscillators are already excited, leading to the Dulong-Petit law. As we will show next, this is not the case, and in fact floppy modes are essential in determining T_g . To show this, we use the Lindemann criteria (1910), which has been originally devised to understand crystal melting [34]. Such criteria establishes that melting occurs when the mean atomic square displacement $\langle u^2(T) \rangle$ is around 10% of the atomic spacing a . There are many experimental evidences that this criteria is applicable to glasses [30], as for example happens with Se and $Se - Ge$ systems [29]. The value of $\langle u^2(T) \rangle$ can be calculated from the density of vibrational states $g(\omega)$. At high temperatures,

$$\langle u^2(T) \rangle = \frac{kT}{mN} \int_0^\infty \frac{g(\omega)}{\omega^2} d\omega \quad (1)$$

where k is the Boltzmann constant, T the temperature, ω the frequency and m the mass. At T_g , the Lindemann criteria applied to glasses [29] establishes that $\langle u^2(T_g) \rangle \approx \langle u^2(T_m) \rangle \approx 0.1a^2$ where T_m is the melting temperature. This shows the fundamental importance of floppy modes to determine T_g due to the enhancement of low frequencies produced by the term ω^{-2} in eq.(1), which leads to an increasing $\langle u^2 \rangle$. Let us made a model for the most prototypical chalcogenide glass: $Se_{1-x-y}Ge_xAs_y$, since this compound allows to obtain the same $\langle r \rangle$ with different chemical compositions. The three chemical elements of this glass have nearly the same mass; thus we can suppose that in eq.(1) all the atomic masses are equal, although in more general cases m must be replaced by an averaged mass. The most simple form for $g(\omega)$ is to use an Einstein like model, with a delta function centered around a characteristic floppy peak at ω_f , with a weight given by the number of floppy modes, plus a density of states that has the rest of the spectral weight. Such a density of states can be written as,

$$g(\omega) = 3N(1 - f)g_I(\omega) + 3Nf\delta(\omega - \omega_f) \quad (2)$$

where $g_I(\omega)$ is a density normalized to one for $f = 0$. It is important to remark that in this model, $g_I(\omega)$ will be the same at all glass compositions below $\langle r \rangle = 2.4$, and the relative weight on non-floppy modes is taken into account by the factor $1 - f$. Note that by using a fixed $g_I(\omega)$ for all chemical compositions, we are overestimating this contribution for flexible glasses, which will give only a small correction to the final result, since $g(\omega)/\omega^2$ goes to zero at high frequencies [33]. This assumption is also supported by the neutron scattering data [33], which shows that $g(\omega)$ follows an isocoordination rule for $Se_{1-x-y}Ge_xAs_y$. Using $g(\omega)$, $\langle u^2(T) \rangle$ turns out to be,

$$\langle u^2(T) \rangle = \frac{3kT}{m} \left[\left\langle \frac{1}{\omega^2} \right\rangle_R + f \left(\frac{1}{\omega_f^2} - \left\langle \frac{1}{\omega^2} \right\rangle_R \right) \right], \quad (3)$$

where $\langle \frac{1}{\omega^2} \rangle_R$ is defined as the second inverse moment at

the rigidity transition,

$$\left\langle \frac{1}{\omega^2} \right\rangle_R \equiv \int_0^\infty \frac{g_I(\omega)}{\omega^2} d\omega$$

Eq.(3) predicts a linear dependence of $\langle u^2(T) \rangle$ upon f . This result and the idea of an Einstein-like mode for floppy modes are supported by the giant-softening of the 119Sn Lamb-Mossbauer factor in $(Ge_{0.99}Sn_{0.01})_xSe_{1-x}$ glasses [16] as x linearly decreases to 0, *i.e.*, as the glass gets more floppy. The mean square displacement at absolute zero or the first moment of the vibrational density of states contains the information on these floppy modes, and its variation x nicely scales with the scattering strength of the 5meV mode observed in inelastic scattering [16].

Now we turn our attention to combine these results with the Lindemann criteria. When $f = 0$, we use eq.(2) and the Lindemann criteria to obtain T_g at the rigidity threshold $f = 0$,

$$T_g(f = 0) \approx \frac{0.1ma^2}{3k \langle \frac{1}{\omega^2} \rangle_R} \quad (4)$$

For the variation of T_g as a function of rigidity, we use the previous expression to rewrite eq.(3) in terms of $T_g(f = 0)$, and then we apply again the Lindemann criteria to obtain,

$$T_g(f) = \frac{T_g(f = 0)}{1 + \alpha f} \quad (5)$$

where $T_g(f)$ is the glass transition temperature when a fraction f of floppy modes is present. The parameter α is defined as,

$$\alpha \equiv \frac{1}{\omega_f^2 \langle \frac{1}{\omega^2} \rangle_R} - 1 \equiv \left(\frac{\Theta_R}{\Theta_f} \right)^2 - 1,$$

and depends upon the ratio of two characteristic frequencies, since we define the following frequency and temperature at the rigidity transition, $\Theta_R/\hbar \equiv \omega_R \equiv \langle \frac{1}{\omega^2} \rangle_R^{-1/2}$.

Equation (5) predicts a decreasing glass temperature with the number of floppy modes. Furthermore, by using the Maxwell mean field to express f in terms of $\langle r \rangle$, eq.(5) can be transformed into,

$$T_g(\langle r \rangle) = \frac{T_g(\langle r \rangle = 2.0)}{1 - \beta (\langle r \rangle - 2.0)}, \quad (6)$$

where the constant β is given by,

$$\beta = \frac{5\alpha}{2\alpha + 6}.$$

The value of $T_g(\langle r \rangle)$ obtained in eq.(6) is exactly in the same form of the empirically modified Gibbs-DiMarzio

equation that has been used as a fitting law for many chalcogenide glasses, where β is a constant taken from the experimental data. Our approach shows that this constant depends upon the ratio of two characteristic frequencies or temperatures. It is worthwhile mentioning that the constant experimental value of β in the interval $2.0 \leq \langle r \rangle \leq 2.4$ gives an extra support to the assumption made in eq.(2). For $\langle r \rangle > 2.4$, the isocoordination rule for T_g is broken and β is no longer constant for different chemical compositions, as is also observed with the glass transition temperature. Another advantage of the approach presented in this letter, is that β can be estimated from neutron scattering data or Lamb-Mossbauer factor. Here we will use the neutron scattering data taken from reference [33]. We start by noting that at the rigidity transition, $f = 0$ and from eq.(3), $g_I(\omega) = g(\omega)$. Thus, $\langle \frac{1}{\omega^2} \rangle_R$ can be obtained from the experimental data by calculating the second inverse moment of the normalized density of states at $\langle r \rangle = 2.4$. Following this procedure, we get $\langle \frac{1}{\omega^2} \rangle_R \approx 0.01986 meV^{-2}$, with a characteristic frequency $\omega_R \approx 7.0959 meV$, and temperature $\Theta_R \approx 76^\circ K$. Using that $\omega_f \approx 5 meV$, α has the approximate value 1.014, and finally $\beta \approx 0.67$. The value from fitting the experimental data of the glass transition has been obtained by many groups [6][7][9], and produce the value $\beta \approx 0.72$ which is in very good agreement with our estimation from neutron data. The calculation of β can be improved by taking into account that the floppy peak is not a delta function, but instead it has a finite width, which will provide a small correction to the result. However, even in this simple first approximation the results are encouraging.

In conclusion, we have explored the effects of floppy modes into the glass transition temperature of glasses. Although these modes are not at zero frequency and at high temperature they do not play a role in the specific heat, they are fundamental to determine the glass transition temperature since they enhance the square mean displacement. Then, by using the Lindemann criteria and a very simple model of the vibrational density of states, we recovered the empirically modified Gibbs-DiMarzio equation that has been widely used to account for the change in the transition temperature of chalcogenide glasses. The constant that appear in this law depends upon two parameters: the frequency of floppy modes and the second inverse moment of the density of non-floppy modes. The results of this letter are in agreement with Phillip's original idea that glass forming tendency is enhanced at the rigidity transition [35][36], as also thermodynamical reversibility [8], since it seems that there is less entropy due to a smaller quadratic displacement.

Acknowledgments. This work was supported by DGAPA UNAM project IN108502, and CONACyT -US National Science Foundation joint project 41538.

-
- [1] P.W. Anderson, Science **267**, 1615 (1995).
- [2] J.C. Phillips, Rep. Prog. Phys. **59** 1133 (1996).
- [3] J. Jackle, Rep. Pro. Phys. **49**, 171 (1986).
- [4] P.G. Debenedetti, Metastable Liquids, Princeton Univ. Press, 1996.
- [5] P.G. Debenedetti and F.H. Stillinger, Nature **410**, 259 (2000).
- [6] M. Tatsumisago, B.L. Halfpap, J.L. Green, S.M. Lindsay, C.A. Angell, Phys. Rev. Lett. **64**, 1549 (1990).
- [7] A.N. Sreeram, D.R. Swiler, A.K. Varshneya, J. Non-Cryst. Solids **127**, 287 (1991).
- [8] D. Selvanathan, W.J. Bresser and P. Boolchand, Phys. Rev. **B61**, 15061 (2000).
- [9] P. Boolchand, D.G. Georgiev, T. Qu, F. Wang, L. Cai, S. Chakravarty, C.R. Chimie **5**, 713 (2002).
- [10] R. Kerner, Physica **B 215**, 267 (1995).
- [11] R. Kerner, G.G. Naumis, J. of Phys: Condens. Matter **12**, 1641 (2000).
- [12] M. Micoulaut, G.G. Naumis, Europhys Lett. **47**, 568 (1999).
- [13] J.C. Phillips, J. Non-Cryst. Solids **34**, 153 (1979).
- [14] M.F. Thorpe, J. Non-Cryst. Solids **57**, 355 (1983).
- [15] H. He and M.F. Thorpe, Phys. Rev. Lett. **54**, 2107 (1985).
- [16] P. Boolchand, *Vibrational Excitations in glasses: rigidity transition and Lamb-Mössbauer Factors*, in: Insulating and semiconducting glasses, ed. by P. Boolchand, World Scientific, Singapore, 2000.
- [17] A. Huerta, G.G. Naumis, Phys. Rev. Lett. **90**, 145701 (2003).
- [18] M.L. Wallace, B. Joós, M. Plischke, Phys. Rev. E **70**, 041501 (2004).
- [19] A. Huerta, G.G. Naumis, D.T. Wasan, D. Henderson, A. Trokhymchuk, J. of Chem. Phys. **120**, 1506 (2004).
- [20] A.J. Rader, Brandon M. Hespenheide, Leslie A. Kuhn, and M.F. Thorpe, PNAS **99**, 3540-3545, (2002).
- [21] P. Boolchand, D.G. Georgiev, M. Micoulaut, J. of Optoelectronics and Advanced Materials **4**, 823 (2002).
- [22] P. Boolchand, et. al., *Evidence for the intermediate phase in chalcogenide glasses*, in: Phase Transitions And Self-Organization in Electronic and Molecular Networks. Ed. J.C. Phillips and M.F. Thorpe, Kluwer Academic/Plenum Publishers, 2001.
- [23] Y. Wang, J. Wells, D.G. Georgiev, P. Boolchand, K. Jackson, M. Micoulaut, Phys. Rev. Lett. **87**, 185503 (2001).
- [24] M.F. Thorpe, D.J. Jacobs, M.V. Chubinsky, and J.C. Phillips, J. Non-Cryst. Solids **266**, 859 (2000).
- [25] J. Barré, A. R. Bishop, T. Lookman, A. Saxena, Phys. Rev. Lett. **94**, 208701 (2005).
- [26] G.G. Naumis, Phys. Rev. B **61**, R9205 (2000).
- [27] A. Huerta, G. G. Naumis, Phys. Lett. **A299**, 660 (2002).
- [28] A. Huerta, G.G. Naumis, Phys. Rev. B **66**, 184204 (2002).
- [29] W.A. Phillips, U. Buchenau, N. Nücker, A.J. Dianoux, W. Petry, Phys. Rev. Lett. **63**, 2381 (1989).
- [30] U. Buchenau, R. Zorn, Europhys. Lett. **18**, 523 (1992).
- [31] M. F. Thorpe, D.J. Jacobs, M.V. Chubynsky and J.C. Phillips, J. Non-Cryst. Solids **266-269**, 859 (2000).
- [32] P. Boolchand, R.N.ENZWEILER, R.L. Capelletti, W.A. Kamitakahara, Y. Cai and M.F. Thorpe, Solids State Ionics **39**, 81 (1990).
- [33] W.A. Kamitakahara, R.L. Capelletti, P. Boolchand, B. Halfpap, F. Gompf, D.A. Neumann, H. Mutka, Phys. Rev. B **44**, 94 (1991).
- [34] D. Tabor, Gases, liquids and solids, Cambridge University Press, Cambridge, 1996.
- [35] J.C. Phillips, in Rigidity Theory and Applications, ed. by J.C. Phillips and P.M. Duxbury, Kluwer Academic/Plenum Publishers, New York, 1999.
- [36] J.C. Phillips, in Phase transitions and Self-Organization in electronic and molecular networks, ed. by J.C. Phillips and M.F. Thorpe, Kluwer Academic/Plenum Publishers, New York, 2001.